



Building with conscience.

Sto Corp.
3800 Camp Creek
Parkway
Building 1400, Suite 120
Atlanta, GA 30331

Tel: 404 346 3666
Toll free: 800 221 2397
Fax: 404 346 3119

STO GUIDE SPECIFICATION SPECIFICATION 82211 – Sto Full-Depth, Pre-extended, Cement-Based, Structural Repair

REPAIR MORTARS

PART 1 - GENERAL

1.01 SUMMARY

- A. Provide repair mortar for horizontal and formed vertical/overhead patch and repair of existing substrates.
- B. Related Sections: Other specification sections which relate directly to the work of this section include the following:
 - 1. Section 03300, Cast-In-Place Concrete.

1.02 SUBMITTALS

- A. Product Data: Submit manufacturer's product data and installation instructions for each material and product used. Include manufacturer's Safety Data Sheets (SDS).

1.03 REFERENCES

- 1. ASTM C109, Compressive Strength
- 2. ASTM C469, Modulus of Elasticity
- 3. ASTM C293, Flexural Strength
- 4. ASTM C157, Drying Shrinkage
- 5. ASTM C309, Specification for Curing Compounds
- 6. ICRI Technical Guideline No. 03732 Specifying Concrete Surface Preparation for Sealers, Coatings, and Polymer Overlays
- 7. ACI 305R, Guide for Hot Weather Concreting
- 8. ACI 306R, Guide for Cold Weather Concreting

1.04 QUALITY ASSURANCE

- A. Manufacturer's Qualifications: The manufacturer shall be a company with at least five years experience and regularly engaged in the manufacture and marketing of products specified herein. The manufacturer shall have an ISO 9001 certified quality system and ISO 14001 environmental management system.
- B. Installer's Qualifications: The contractor shall be qualified to perform the work specified by reason of experience.
- C. Job Site: Verify bond to properly prepared substrates as specified by design professional.

1.05 DELIVERY, STORAGE AND HANDLING

- A. Deliver products in original packaging, labeled with product identification, manufacturer, batch number and shelf life.
- B. Store products in a dry area with temperature maintained between 50 and 85 degrees F(10 and 29 degrees C). Protect from direct sunlight.
- C. Handle products in accordance with manufacturer's printed recommendations.

PART 2 - PRODUCTS

2.02 MATERIALS

- A. Horizontal repair mortar: Single-component, cement-based repair mortar, containing portland cement, graded specialty aggregates, and admixtures. Comply with the following:

Manufacturer: 82211 Sto Full-Depth as manufactured by Sto Corp. 3800 Camp Creek Parkway, Building 1400, Suite 120, Atlanta, Georgia 30331

- 1. Performance and Physical Properties: Meet or exceed the following values for material cured at 73 degrees F and 50 percent relative humidity:
 - a. Working Time: 20 – 40 minutes.
 - b. Compressive Strength per ASTM C109: 4,500 psi (31.0 MPa) at 7 days, 6,000 psi (41.4 MPa) at 28 days
 - c. Modulus of Elasticity per ASTM C469: 3.6×10^6 psi (24.8×10^3 MPa) at 28 days
 - d. Flexural Strength per ASTM C293: 690 psi (4.76 MPa) at 7 days, 725 psi (5.0 MPa) at 28 days
 - e. Shrinkage per ASTM C157 mod.: Less than 0.079% at 28 days, air cured.
 - f. Color: Concrete gray.

PART 3 – EXECUTION

3.01 INSTALLATION OF FULL DEPTH REPAIR MORTAR:

- A. Examine substrates and conditions under which materials will be installed. Do not proceed with installation until all unsatisfactory conditions are corrected.
- B. Coordinate installation with adjacent work to ensure proper sequence of construction. Protect adjacent areas and landscaping from contact due to mixing and handling of materials.
- C. Surface Preparation: Comply with manufacturer's printed instructions and the following.
 - 1. Remove loose and deteriorated materials from surfaces to be patched using mechanical chipping, bush-hammering, or hydrodemolition to obtain an ICRI Concrete Surface Profile CSP 5 or greater.
 - 2. Saw-cut or chip the edge of the patch to a right angle with concrete surface. Do not feather edge.
 - 3. Clean surfaces of bond-inhibiting materials including oil, dust and dirt, laitance and standing water.
 - a. If hydrodemolition is used, cement and particulate slurry must be removed from the prepared surfaces before the slurry hardens.
- D. Mixing: Comply with manufacturer's printed instructions and the following.
 - 1. Precondition components to temperature of 70 degrees F plus or minus 5 degrees F (21 degrees C plus or minus 2.5 degrees C) prior to mixing.
 - 2. Add 4.8 to 5.3 pints (2.3 to 2.5 L) of clean water per 65-pound (29.5-kg) bag.
 - 3. Mix using a mechanical mixer to a uniform, lump-free consistency. Avoid over-mixing.
 - 4. Do not add water beyond manufacturer's instructions. Do not add additional powder.

- E. Application: Comply with manufacturer's printed instructions and the following.
 - 1. Apply when ambient and surface temperatures are 45 degrees F (7.5 degrees C) and rising.
 - 2. Comply with applicable sections of ACI 305R and ACI 306R and applicable published product limitations or hot and cold weather application.
 - 3. Dampen substrate to fill concrete pores with water. Remove ponding, glistening, or surface water (saturated surface dry).
 - 4. Apply scrub coat of repair mortar into substrate to ensure intimate contact and establish bond.
 - a. Alternatively, prepared concrete and reinforcing steel may be primed using Sto Bonding and Anti-Corrosion Agent.
 - 5. Apply mortar while scrub coat is wet. Consolidate and trowel to the desired finish, with a minimum thickness of 1-inch (25mm).
 - 6. Vibrate closed-form repairs to ensure intimate contact with the substrate, establish bond, and ensure proper consolidation. Avoid over-vibration.
- F. Curing
 - 1. Keep surface damp for 48 hours with continuous light water fogging.
 - 2. If no coating or sealer is to be applied, a water-based curing compound meeting ASTM standard C309 may be used.
 - 3. Do not use solvent-based curing compounds.
 - 4. Comply with applicable sections of ACI 305R and ACI 306R for hot and cold weather curing.
- G. Cleaning: Remove excess material before material cures. If material has cured, remove using mechanical methods that will not damage substrate.

END OF SECTION

ATTENTION

Sto products are intended for use by qualified professional contractors, not consumers, as a component of a larger construction assembly as specified by a qualified design professional, general contractor or builder. They should be installed in accordance with those specifications and Sto's instructions. Sto Corp. disclaims all, and assumes no, liability for on-site inspections, for its products applied improperly, or by unqualified persons or entities, or as part of an improperly designed or constructed building, for the nonperformance of adjacent building components or assemblies, or for other construction activities beyond Sto's control. Improper use of Sto products or use as part of an improperly designed or constructed larger assembly or building may result in serious damage to Sto products, and to the structure of the building or its components. STO CORP. DISCLAIMS ALL WARRANTIES EXPRESS OR IMPLIED EXCEPT FOR EXPLICIT LIMITED WRITTEN WARRANTIES ISSUED TO AND ACCEPTED BY BUILDING OWNERS IN ACCORDANCE WITH STO'S WARRANTY PROGRAMS WHICH ARE SUBJECT TO CHANGE FROM TIME TO TIME. For the fullest, most current information on proper application, clean-up, mixing and other specifications and warranties, cautions and disclaimers, please refer to the Sto Corp. website, www.stocorp.com.

Copyright 2020 Sto Corporation. All Rights Reserved.

A copyright license to reproduce this specification is granted to specifying architects and engineers.